

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 December 2006 (07.12.2006)

PCT

(10) International Publication Number
WO 2006/128646 A2

(51) International Patent Classification:
C08L 23/00 (2006.01)

(74) Agent: VELDHUIZEN, A., D., W.; ExxonMobil Chemical Europe Inc., P.O. Box 105, B-1830 Machelen (BE).

(21) International Application Number:
PCT/EP2006/005064

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 24 May 2006 (24.05.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0511320.4 3 June 2005 (03.06.2005) GB

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS INC.** [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US).

Published:

— without international search report and to be republished upon receipt of that report

(71) Applicant (for GB only): **EXXONMOBIL CHEMICAL LIMITED** [GB/GB]; P.O. Box 122, 4600 Parkway, Solent Business Park, Whiteley Fareham, Hampshire PO15 7AP (GB).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(72) Inventor; and

(75) Inventor/Applicant (for US only): **JOURDAIN, Eric** [FR/BE]; Avenue Simonne 22, B-1640 Rhode Saint Genese (BE).



WO 2006/128646 A2

(54) Title: ELASTOMERIC STRUCTURES

(57) Abstract: The invention relates to elastomeric structures comprising first and second members, each of a different elastomeric material, in which the first member includes a modifier. The shaped structure may be, for example, an automotive weatherseal.

ELASTOMERIC STRUCTURES

This invention relates to elastomeric structures, especially structures comprising two or more parts adhered together, such as weatherseals, and to a
5 process of making such structures.

Elastomeric compositions are widely used in such applications as automobile parts, cables, and building and construction seals. In some cases, it is desirable to use a structure comprising two or more parts bonded together, each part being of a different elastomeric composition. For example, weatherseals for
10 use in sealing automobile windows can include an extruded profile of cured EPDM (ethylene/propylene/diene monomer polymer) material onto which has been molded a TPE (thermoplastic elastomer) material. Frequently, the adhesion between the two materials is critical to the successful functioning of the article. It has been found, however, that a difference in properties or characteristics of the
15 surfaces of the two compositions may cause difficulty in effecting bonding between them. There remains a need for an improved method of producing a structure having two dissimilar elastomeric materials, and for an improvement in such structures. The adhesion of a TPE material onto cured EPDM material is generally weak, and combinations of those materials therefore represent a special
20 problem.

Addition of a plasticizer or other amorphous substance to a polyolefin is one way to modify their properties. For example, polyolefins and elastomers are blended with materials such as mineral oils which contain aromatic and/or other functional groups. Typically, addition of mineral oil also lowers the melt viscosity
25 because the mineral oil itself has a viscosity well below that of the polyolefin.

Addition of compounds like mineral oils tend to improve the flexibility of a polyolefin, which identifies such compounds as "plasticizers" under the commonly accepted definition; that is, a substance that improves the flexibility, workability, or distensibility of a plastic or elastomer. Mineral oils are
30 also often used as extenders, as well as for other purposes, in polyolefins.

To improve the low temperature characteristics, it is customary to choose

lower molecular weight, amorphous compounds as plasticizers. Low molecular weight compounds are also chosen for their low viscosity, which typically translates into lower melt viscosity and improved processibility of the polyolefin composition. Unfortunately, this choice often leads to other problems. For example, all or some of the additive can migrate to a surface and evaporate at an unacceptably high rate, which results in deterioration of properties over time. If the flash point is sufficiently low (e.g., less than 200°C), the compound can cause smoking and be lost to the atmosphere during melt processing. It can also leach out of the polyolefin and impair food, clothing, and other articles that are in contact with the final article made from the plasticized polyolefin. It can also cause problems with tackiness or other surface properties of the final article.

Another shortcoming of typical additive compounds is that they often contain a high (greater than 5 wt%) degree of functionality due to carbon unsaturation and/or heteroatoms, which tends to make them reactive, thermally unstable, and/or incompatible with polyolefins, among other things. Mineral oils, in particular, consist of thousands of different compounds, many of which are undesirable for use in polyolefins due to molecular weight or chemical composition. Under moderate to high temperatures these compounds can volatilize and oxidize, even with the addition of oxidation inhibitors. They can also lead to problems during melt processing and fabrication steps, including degradation of molecular weight, cross-linking, or discoloration.

These attributes of typical additive compounds like mineral oils limit the performance of the final plasticized polyolefin, and therefore its usefulness in many applications. As a result, they are not highly desirable for use as modifiers for polyolefins.

There remains a need for improved articles in which the adhesion between differing materials is enhanced, and for ways of making such articles.

In a first aspect, the invention provides a structure comprising a first member of a first elastomeric material and a second member of a second elastomeric material, different from the first, adhering to the first member, wherein at least the first member comprises a modifier which comprises carbon

and hydrogen, and does not contain an appreciable extent of functional groups and has one or more of the following characteristics:

- a. a pour point (ASTM D97) of -10°C or less;
- b. Viscosity Index (VI) as measured by ASTM D2270 of 120 or more;
- 5 c. a flash point (ASTM D92) of 200°C or more;
- d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.

In a second aspect, the invention provides a process of making a shaped elastomeric structure comprising the steps of compounding and shaping a first elastomeric material and a modifier as defined above to give a first member and
10 then applying onto that first member a second elastomeric material to give a second member adhering to the first member.

Whilst not wishing to be limited by any theory, it is believed that the presence of the modifier in the first elastomeric material promotes the creation of domains at the material surface which are amorphous, uncured and thermo-
15 sensitive, especially where that material is an EPDM material, which in turn promotes the physical interaction with the second elastomeric material during the bonding process.

In both aspects of the invention, the second elastomeric material may also comprise a modifier. It is believed that the presence of a modifier in both first and
20 second elastomeric materials may further promote effective bonding between those two materials.

The modifier of the second elastomeric material may be the same or different to that of the first elastomeric material. Optionally, it is the same.

The shaped structure may also comprise one or more other members which
25 may be of the same material as either the first or the second members or may be of one or more other materials. For example, the shaped structure may comprise two members of the same EPDM material with a member of TPE material bonded between them. In that case, one, two or all of the members may comprise a modifier.

30 In a preferred embodiment, the modifier has a flash point (ASTM D92) of 200°C or more, and one or more of:

- a. a pour point (ASTM D97) of -10°C or less;
- b. a Viscosity Index (VI) as measured by ASTM D2270 of 120 or more;
- d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.

In an alternative preferred embodiment, the modifier has

- 5 b. a Viscosity Index (VI) as measured by ASTM D2270 of 120 or more;
- and
- d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.

The modifier is preferably a liquid modifier.

It will be realized that the classes of materials described herein that are
10 useful as modifiers can be utilized alone or admixed with other modifiers described herein in order to obtain desired properties.

The modifier of the present invention is preferably a compound comprising carbon and hydrogen, and preferably does not contain an appreciable extent of functional groups selected from hydroxide, aryls and substituted aryls,
15 halogens, oxygen-containing groups such as alkoxys, carboxylates, carboxyl, esters, acrylates and ethers, and nitrogen-containing groups such as amines. By "appreciable extent of functional groups", it is meant that compounds comprising these groups are not deliberately added to the modifier, and if present at all, are present at less than 5 weight % (wt%) in one embodiment, more preferably less
20 than 4 wt%, more preferably less than 3 wt%, more preferably less than 2 wt%, more preferably less than 1 wt%, more preferably less than 0.7 wt%, more preferably less than 0.5 wt%, more preferably less than 0.3 wt%, more preferably less than 0.1 wt%, more preferably less than 0.05 wt%, more preferably less than 0.01 wt%, more preferably less than 0.001 wt%, where wt% is based upon the
25 weight of the modifier.

Preferably, the modifier has a total content of carbon and hydrogen, as determined by elemental analysis, of at least 95%, more preferably at least 96%, more preferably at least 97%, more preferably at least 98%, more preferably at least 99%, more preferably at least 99.3%, more preferably at least 99.9%, and
30 more preferably at least 99.95% by weight.

In another embodiment, the modifier is a hydrocarbon that does not

contain olefinic unsaturation to an appreciable extent. By "appreciable extent of olefinic unsaturation" it is meant that the carbons involved in olefinic bonds account for less than 10 %, preferably less than 9 %, more preferably less than 8 %, more preferably less than 7 %, more preferably less than 6 %, more preferably less than 5 %, more preferably less than 4 %, more preferably less than 3 %, more preferably less than 2 %, more preferably less than 1 %, more preferably less than 0.7 %, more preferably less than 0.5 %, more preferably less than 0.3 %, more preferably less than 0.1 %, more preferably less than 0.05 %, more preferably less than 0.01 %, more preferably less than 0.001 %, of the total number of carbons.

10 In some embodiments, the percent of carbons of the modifier involved in olefinic bonds is between 0.001 and 10 % of the total number of carbon atoms in the modifier, preferably between 0.01 and 7 %, preferably between 0.1 and 5 %, more preferably less than 1 %. Percent of carbons involved in olefinic bonds is determined by ¹H NMR spectroscopy.

15 In one embodiment, the modifier of the present invention comprises C25 to C1500 paraffins, and C30 to C500 paraffins in another embodiment. In another embodiment, the modifier consists essentially of C35 to C300 paraffins, and consists essentially of C40 to C250 paraffins in another embodiment.

In one embodiment, the modifier of the present invention has a pour point (ASTM D97) of less than -10°C in one embodiment, less than -20°C in another embodiment, less than -30°C in yet another embodiment, less than -40°C in yet another embodiment, less than -50°C in yet another embodiment, and less than -60°C in yet another embodiment, and greater than -120°C in yet another embodiment, and greater than -200°C in yet another embodiment, wherein a desirable range may include any upper pour point limit with any lower pour point limit described herein.

25

Any modifier described herein may have a Viscosity Index (VI) as measured by ASTM D2270 of 90 or more, preferably 95 or more, more preferably 100 or more, more preferably 105 or more, more preferably 110 or more, more preferably 115 or more, more preferably 120 or more, more preferably 125 or more, more preferably 130 or more. In another embodiment the modifier has a VI

30

between 90 and 400, preferably between 120 and 350.

In some embodiments, the modifier may have a kinematic viscosity at 100°C (ASTM D445) of from 3 to 3000 cSt, and from 6 to 300 cSt in another embodiment, and from 6 to 200 cSt in another embodiment, and from 8 to 100 cSt
5 in yet another embodiment, and from 4 to 50 cSt in yet another embodiment, and less than 50 cSt in yet another embodiment, and less than 25 cSt in yet another embodiment, wherein a desirable range may comprise any upper viscosity limit with any lower viscosity limit described herein.

In another embodiment any modifier described herein may have a flash
10 point (ASTM D92) of 200°C or more, preferably 210° or more, preferably 220°C or more, preferably 230°C or more, preferably 240°C or more, preferably 245°C or more, preferably 250°C or more, preferably 260°C or more, preferably 270°C or more, preferably 280°C or more. In another embodiment the modifier has a flash point between 200°C and 300°C, preferably between 240°C and 290°C.

15 Any modifier described herein may have a dielectric constant measured at 20°C of less than 3.0 in one embodiment, and less than 2.8 in another embodiment, less than 2.5 in another embodiment, and less than 2.3 in yet another embodiment, and less than 2.1 in yet another embodiment.

In some embodiments any modifier described herein may have a specific
20 gravity (ASTM D4052, 15.6/15.6oC) of less than 0.88 in one embodiment, and less than 0.87 in another embodiment, and less than 0.86 in another embodiment, and less than 0.85 in another embodiment, and from 0.80 to 0.87 in another embodiment, and from 0.81 to 0.86 in another embodiment, and from 0.82 to 0.85 in another embodiment, wherein a desirable range may comprise any upper
25 specific gravity limit with any lower specific gravity limit described herein.

Any modifier described herein preferably has a low degree of color, such as typically identified as “water white”, “prime white”, “standard white”, or “bright and clear,” preferably an APHA color of 100 or less, preferably 80 or less, preferably 60 or less, preferably 40 or less, preferably 20 or less, as determined by
30 ASTM D1209.

The modifier preferably has a number average molecular weight (Mn) of

21,000 g/mole or less in one embodiment, preferably 20,000 g/mole or less, preferably 19,000 g/mole or less, preferably 18,000 g/mole or less, preferably 16,000 g/mole or less, preferably 15,000 g/mole or less, preferably 13,000 g/mole or less and 10,000 g/mole or less in yet another embodiment, and 5,000 g/mole or less in yet another embodiment, and 3,000 g/mole or less in yet another embodiment, and 2,000 g/mole or less in yet another embodiment, and 1500 g/mole or less in yet another embodiment, and 1,000 g/mole or less in yet another embodiment, and 900 g/mole or less in yet another embodiment, and 800 g/mole or less in yet another embodiment, and 700 g/mole or less in yet another embodiment, and 600 g/mole or less in yet another embodiment, and 500 g/mole or less in yet another embodiment. Preferred minimum Mn is at least 200 g/mole, preferably at least 300 g/mole. Further a desirable molecular weight range can be any combination of any upper molecular weight limit with any lower molecular weight limit described above. Mn is determined using size exclusion chromatography in 1,2,4-trichlorobenzene stabilised with butylated hydroxytoluene on three Polymer Laboratories PLgel 10 mm Mixed-B columns with a differential refractive index detector, an online light scattering detector and a viscometer.

Certain mineral oils have been classified as Hydrocarbon Basestock Group I, II, or III by the American Petroleum Institute (API) according to the amount of saturates and sulfur they contain and their viscosity indices. Group I basestocks are solvent-refined mineral oils that contain the highest levels of unsaturates and sulfur, and low viscosity indices; they tend to define the bottom tier of lubricant performance. They are the least expensive to produce and currently account for the bulk of the "conventional" basestocks. Groups II and III basestocks are more highly refined (e.g., by hydroprocessing) than Group I basestocks, and often perform better in lubricant applications. Group II and III basestocks contain less unsaturates and sulfur than the Group I basestocks, while Group III basestocks have higher viscosity indices than the Group II basestocks do. Additional API basestock classifications, namely Groups IV and V, are also used in the basestock industry. Group IV basestocks include polyalphaolefins. The five basestock

groups are described by Rudnick and Shubkin in Synthetic Lubricants and High-Performance Functional Fluids, Second edition (Marcel Dekker, Inc. New York, 1999). The modifier may be a group III or group IV basestock.

In a preferred embodiment, the modifier is a polyalphaolefin. As
5 polyalphaolefin (PAO), there may advantageously be used an oligomer of an
alphaolefin having from 5 to 14 carbon atoms, e.g., 1-pentene, 1-hexene, 1-
heptene, 1-octene, 1-nonene, 1-decene, 1-undecene and 1-dodecene. Preferred
oligomers are of alphaolefins having from 6 to 12, more preferred are those having
from 8 to 12, carbon atoms, and most preferred are oligomers of the C10
10 alphaolefin 1-decene. The materials may be, and usually are, mixtures of different
oligomers of the same olefin, and they may be mixtures of oligomers of more than
one olefin. The PAO may be hydrogenated, to remove all or substantially all
residual double bonds.

Advantageously, the PAO has a number average molecular weight (Mn)
15 within the range of from 100 to 21000, more advantageously from 200 to 10000,
preferably from 200 to 7000, more preferably from 200 to 5000, and most
preferably from 1000 to 4000. Advantageously, it has a pour point below 0°C,
more advantageously below -10°C, preferably below -20°C, and most preferably
below -30°C.

20 Preferably, the PAO's have a kinematic viscosity at 100°C of 3 cSt or more,
preferably 6 cSt or more, preferably 8 cSt or more, preferably 10 cSt or more,
preferably 20 cSt or more, preferably 300 cSt or less, preferably 100 cSt or less.
Advantageously, the PAO's have a kinematic viscosity at 100°C of between 3 and
1000 cSt, preferably between 6 and 300 cSt, preferably between 8 and 100 cSt,
25 preferably between 8 and 40 cSt.

Preferably, the PAO's have a Viscosity Index of 120 or more, preferably
130 or more, preferably 140 or more, preferably 150 or more, preferably 170 or
more, preferably 200 or more, preferably 250 or more.

Preferably, the PAO's have a flash point of 200°C or more, preferably
30 220°C or more, preferably 240°C or more, preferably between 260°C and 290°C.

Examples of suitable commercially available PAO's are those in the

Spectrasyn, SHF, and SuperSyn (trademarks) series of ExxonMobil Chemical Company. Other PAO materials available include those sold under the Synfluid trademark by Chevron Phillips Chemical Co, under the Durasyn trademark by BP Amoco Chemicals, under the Nexbase trademark by Fortum Oil and Gas, under the Synton trademark by Crompton Corporation, and under the Emery trademark by Cognis Corporation.

In another embodiment, the modifier is a hydrocarbon fluid with a branched paraffin : normal paraffin ratio ranging from about 0.5:1 to 9:1, preferably from about 1:1 to 4:1. The branched paraffins of the mixture contain greater than 50 wt% (based on the total weight of the branched paraffins) mono-methyl species, for example, 2-methyl, 3-methyl, 4-methyl, 5-methyl or the like, with minimum formation of branches with substituent groups of carbon number greater than 1, such as, for example, ethyl, propyl, butyl or the like; preferably, greater than 70 wt% of the branched paraffins are mono-methyl species. The paraffin mixture has a number-average carbon number (Cn) in the range of 20 to 500, preferably 30 to 400, preferably 40 to 200, preferably 25 to 150, preferably 30 to 100, more preferably 20 to 100, more preferably 20 to 70; has a kinematic viscosity at 100°C ranging from 3 to 500 cSt, preferably 6 to 200 cSt, preferably 8 to 100 cSt, more preferably 6 to 25 cSt, more preferably 3 to 25 cSt, more preferably 3 to 15 cSt; and boils within a range of from 100 to 350°C, preferably within a range of from 110 to 320°C, preferably within a range of 150 to 300°C. In a preferred embodiment, the paraffinic mixture is derived from a Fischer-Tropsch process. These branch paraffin/n-paraffin blends are described in, for example, US 5,906,727.

Thus, the modifier may comprise a wax isomerate lubricant oil basestock, which includes hydroisomerized waxy stocks (e.g. waxy stocks such as gas oils, slack waxes, fuels hydrocracker bottoms, etc.), hydroisomerized Fischer-Tropsch hydrocarbons and waxes, Gas-to-Liquids (GTL) base stocks and base oils, and other waxy feedstock derived hydroisomerized base stocks and base oils, or mixtures thereof. Fischer-Tropsch waxes, the high boiling point residues of Fischer-Tropsch synthesis, are highly paraffinic hydrocarbons with very low sulfur

content, and are often preferred feedstocks in processes to make hydrocarbon fluids of lubricating viscosity.

The hydroprocessing used for the production of such base stocks may use an amorphous hydrocracking/hydroisomerization catalyst, such as one of the specialized lube hydrocracking catalysts or a crystalline hydrocracking / hydroisomerization catalyst, preferably a zeolitic catalyst. For example, one useful catalyst is ZSM-48 as described in U.S. Patent 5,075,269. Processes for making hydrocracked / hydroisomerized distillates and hydrocracked / hydroisomerized waxes are described, for example, in U.S. Patents Nos. 2,817,693; 4,975,177; 4,921,594 and 4,897,178 as well as in British Patent Nos. 1,429,494; 1,350,257; 1,440,230 and 1,390,359. Particularly favorable processes are described in European Patent Application Nos. 464546 and 464547. Processes using Fischer-Tropsch wax feeds are described in US 4,594,172 and 4,943,672.

Gas-to-Liquids (GTL) base stocks and base oils, Fischer-Tropsch hydrocarbon derived base stocks and base oils, and other waxy feedstock derived base stocks and base oils (or wax isomerates) that can be advantageously used in the present invention have a kinematic viscosities at 100°C of about 3 cSt to about 500 cSt, preferably about 6 cSt to about 200 cSt, preferably about 8 cSt to about 100 cSt, more preferably about 3 cSt to about 25 cSt. These Gas-to-Liquids (GTL) base stocks and base oils, Fischer-Tropsch hydrocarbon derived base stocks and base oils, and other waxy feedstock derived base stocks and base oils (or wax isomerates) have pour points (preferably less than -10°C, preferably about -15°C or lower, preferably about -25°C or lower, preferably -30°C to about -40°C or lower); have a high viscosity index (preferably 110 or greater, preferably 120 or greater, preferably 130 or greater, preferably 150 or greater); and are typically of high purity (high saturates levels, low-to-nil sulfur content, low-to-nil nitrogen content, low-to-nil aromatics content, low bromine number, low iodine number, and high aniline point). Useful compositions of Gas-to-Liquids (GTL) base stocks and base oils, Fischer-Tropsch hydrocarbon derived base stocks and base oils, and wax isomerate hydroisomerized base stocks and base oils are recited in U.S. Patent Nos. 6,080,301; 6,090,989, and 6,165,949 for example, and are

incorporated herein in their entirety by reference.

The modifier may comprise a Group III hydrocarbon basestock, for example, a severely hydrotreated mineral oil having a saturates levels of 90% or more, preferably 92 % or more, preferably 94 % or more, preferably 95% or more.

5 Preferably, the Group III basestock has a sulfur content of less than 0.03 %, preferably between 0.001 and 0.01%. Preferably, the Group III basestock has a VI in excess of 120, preferably 130 or more. Preferably the Group III hydrocarbon base stock has a kinematic viscosity at 100°C of 3 to 100, preferably 4 to 100 cSt, preferably 6 to 50 cSt, preferably 8 to 20; and/or a number average molecular
10 weight of 300 to 5,000, preferably 400 to 2,000, more preferably 500 to 1,000; and/or a carbon number of 20 to 400, preferably 25 to 400, preferably 35 to 150, more preferably 40 to 100. Preferably the Group III basestock has a pour point of -10°C or less. Advantagously, the Group III basestock has a flash point of 200°C or more.

15 Preferably, the modifier is not an oligomer or polymer of C4 olefin(s) (including all isomers, e.g. n-butene, 2-butene, isobutylene, and butadiene, and mixtures thereof). Such materials, which are referred to as “polybutene” liquids (or “polybutenes”) when the oligomers comprise isobutylene and/or 1-butene and/or 2-butene, are commonly used as additives for polyolefins; e.g. to introduce
20 tack or as a processing aid. The ratio of C4 olefin isomers can vary by manufacturer and by grade, and the material may or may not be hydrogenated after synthesis. Commercial sources of polybutenes include BP (Indopol grades) and Infineum (C-Series grades). When the C4 olefin is exclusively isobutylene, the material is referred to as “polyisobutylene” or PIB. Commercial sources of PIB
25 include Texas Petrochemical (TPC Enhanced PIB grades). When the C4 olefin is exclusively 1-butene, the material is referred to as “poly-n-butene” or PNB.

Optionally, the modifier is not an oligomer or polymer of C4 olefin(s); however, an oligomer or polymer of C4 olefin(s) (including all isomers, e.g. n-butene, 2-butene, isobutylene, and butadiene, and mixtures thereof) may be
30 present in the composition. In a preferred embodiment, the composition comprises less than 50 wt% (preferably less than 40%, preferably less than 30

wt%, preferably less than 20 wt%, more preferably less than 10 wt%, more preferably less than 5 wt%, more preferably less than 1 wt%, preferably 0 wt%) polymer or oligomer of C4 olefin(s) such as PIB, polybutene, or PNB, based upon the weight of the composition.

- 5 In a preferred embodiment, the modifier contains less than 50 weight % of C4 olefin(s), preferably isobutylene, based upon the weight of the modifier. Preferably the modifier contains less than 45 weight %, preferably less than 40 wt%, preferably less than 35 wt%, preferably less than 30 wt%, preferably less than 25 wt %, preferably less than 20 wt%, preferably less than 15 wt%,
10 preferably less than 10 wt %, preferably 5 wt%, preferably less than 4 wt %, preferably less than 3%, preferably less than 2%, preferably less than 1 wt%, preferably less than 0.5 wt%, preferably less than 0.25 wt % of C4 olefin(s), preferably isobutylene, based upon the weight of the modifier.

Accordingly, the modifier is preferably:

- 15 a polyalphaolefin;
- i) a hydrocarbon fluid with a branched paraffin: normal paraffin ratio ranging from 0.5:1 to 9:1;
 - ii) a wax isomerate lubricant oil basestock;
 - iii) a Gas-to-Liquids basestock or base oil or a Fischer-
- 20 Tropisch hydrocarbon derived basestock or base oil; or
- iv) a Group III hydrocarbon basestock.
- i), iv) and v) are particularly preferred.

- The first and second (and any other) members may be of any suitable elastomeric materials. The elastomeric materials may include natural elastomers,
25 for example, natural rubber, or they may be synthetic. Preferably, the first and second elastomeric materials include synthetic polymeric elastomeric materials. Those synthetic polymeric elastomeric materials of the first and/or second elastomeric materials may be cured or cross-linked. Alternatively, the synthetic polymeric materials of the first and/or second elastomeric materials may be
30 thermoplastic. Examples of preferred elastomeric polymers include, but are not limited to, ethylene/propylene rubber (EPR), ethylene/propylene/diene

monomer rubber (EPDM), styrenic block copolymer rubbers (including SEBS, SI, SIS, SB, SBS, SIBS and the like, where S = styrene, EB = random ethylene + butene, I = isoprene, and B = butadiene), butyl rubber, halobutyl rubber, copolymers of isobutylene and para-alkylstyrene, halogenated copolymers of
5 isobutylene and para-alkylstyrene, natural rubber, polyisoprene, copolymers of butadiene with acrylonitrile, polychloroprene, alkyl acrylate rubber, chlorinated isoprene rubber, acrylonitrile chlorinated isoprene rubber, polybutadiene rubber (both cis and trans).

The first and second elastomeric materials may include an
10 ethylene/alphaolefin copolymer. Such copolymers include those sold by ExxonMobil Chemical Company under the name EXACT™ and are referred to as plastomers.

In an especially preferred embodiment, the first elastomeric material includes a cross-linked elastomeric polymer material, especially an
15 ethylene/alpha-olefin/diene monomer terpolymer such as an EPDM, and the second elastomeric material includes a thermoplastic elastomeric polymeric material, such as a TPE. Thus, the first elastomeric material may be a compounded or non-compounded cross-linked non-thermoplastic elastomer, such as an EPDM and the second elastomeric material may be a compounded or non-
20 compounded TPE.

Ethylene/alpha-olefin/diene monomer terpolymers are derived from ethylene, one or more alpha-olefins, and one or more non-conjugated diene monomers. The preferred ethylene content is from about 35 to about 85 weight percent, based on the total weight of the ethylene/alpha-olefin/diene monomer
25 terpolymer, preferably from about 40 to about 80 weight percent, and more preferably from about 55 to about 75 weight percent.

The diene monomer may be one or more non-conjugated dienes containing 30 carbon atoms or less, more preferably 20 carbon atoms or less. The preferred non-conjugated dienes include, but are not limited to one or more of 5-ethylidene-
30 2-norbornene (ENB); 1,4-hexadiene; 1,6-octadiene; 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; vinylnorbornene; dicyclopentadiene; and combinations

thereof. The preferred non-conjugated diene content is from about 1 to about 15 weight percent, based on the total weight of the ethylene/alpha-olefin/diene monomer terpolymer, and preferably from about 5 to about 11 weight percent.

Alpha-olefin will make up the remainder of the ethylene/alpha-olefin/diene monomer terpolymer, with percentages adding up to 100 weight percent. The preferred alpha-olefins include, but are not limited to C3, C4, C6, C8, and higher molecular weight alpha-olefins. More preferably, the alpha-olefin is propylene.

The molecular weight of ethylene/alpha-olefin/diene monomer terpolymers is often described with reference to the Mooney viscosity of the base terpolymer (that is, comprising no additives such as oil and carbon black) measured as ML (1+4, 125°C). Typical Mooney viscosity of the base polymer is in the range of 5 to 300 Mooney units (MU), and is preferably in the range of from 50 to 200 MU.

Ethylene/alpha-olefin/diene monomer terpolymers can be prepared using a conventional polymerization process, including traditional Ziegler-Natta catalysts, as well as metallocene catalysts. Synthesis of ethylene/alpha-olefin/diene monomer terpolymers is well known in the art. Reference may be had to G. ver Strate, Encyclopedia of Polymer Science and Engineering, vol. 6, 2nd Ed., 1986, pp. 522-564.

In one embodiment, the rubber component is Vistalon™ 7500 available from ExxonMobil Chemical Company, Houston, Texas. Vistalon™ 7500 is a polymer of ethylene-propylene-ethylidene norbornene having an ethylene content of about 55 weight percent and an ethylidene norbornene content of about 5 weight percent.

Advantageously, the second elastomeric material includes a TPE. The TPE may be, for example, a dispersion of a rubber. Examples of rubbers suitable for use as the dispersed phase in a TPE are one or more of styrene-butadiene (SBR), butadiene-acrylonitrile (NBR) isobutene-isoprene (IIR), and butadiene (BR). The dispersed rubber is preferably one which is vulcanizable during formation of the composition in the melt (dynamically vulcanizable) such as an EPDM, in an olefin polymer, for example, a propylene polymer or an ethylene/propylene copolymer. TPEs which comprise a vulcanised dispersed

phase are referred to as TPE-Vs.

The term “dynamic vulcanization” is herein intended to include a vulcanization process in which an engineering resin and a vulcanizable elastomer are vulcanized under conditions of high shear. As a result, the vulcanizable elastomer is simultaneously cross-linked and dispersed as fine particles of a “micro gel” within the engineering resin. Procedures for dynamically vulcanizing materials are disclosed in U.S. Patent No. 6,013,727, Col. 2, line 57 – Col. 3, line 5, Col. 11, line 4 – Col. 13, line 63 and the examples therein. Examples of TPEs are disclosed in U.S. Patent No. 6,147,180, at Col. 1, lines 17 – Col. 2, line 30, and Col. 3, line 3 – Col. 8, line 5 and the examples therein.

Preferred TPEs are TPE-V (dynamically vulcanized), TPE-S (styrene-containing block copolymers, e.g., styrene-butadiene-styrene (SBS), styrene ethylene/butadiene styrene (SEBS) and styrene-isoprene-styrene (SIPS) block copolymers), TPE-O (polyolefin based, non-vulcanized) TPE-U (polyurethane), TPE-A (polyimide based) and TPE- (polyester based). For a weatherseal, the most preferred material is TPE-V. TPE-A is suitable for use in, for example, automobile hoses. TPE-E is preferred for use in automotive gaiters and boots.

Advantageously, the TPE has a hardness in the range of from 50 to 90 Shore A (test method ISO 868,15s). Advantageously, the TPE has a tensile strength in the range of from 4 to 8 MPa (test method ISO 37/ASTM D 412). Preferably, the TPE has an elongation at break in the range of from 400 to 700% (test method, ISO 37/ASTM D 412). Preferably, the TPE has a compression set 22 hours at 70°C of between 25 and 70% (test method, ISO 815 Type A/ASTM D 395, Method B, Type 1).

The polymers of the first and second elastomeric materials may differ by being in different categories of polymers, or may differ by being different examples of the same category. They may also be the same polymer, but differing in, for example, molecular weight, degree of branching or presence of additives. The invention is, however, especially applicable where the materials of the first and second members are of different categories, for example, if one member is a cured elastomer polymer and another is a thermoplastic elastomer polymer.

The first elastomeric material and the second elastomeric material may each comprise an elastomeric polymer material, such as an EPDM, preferably compounded with one or more other ingredients. Typical ingredients used to compound EPDM for extrusion and cure in order to produce a weatherseal profile
5 are as follows:

Carbon black may be included. Typically carbon blacks are produced from the combustion of gas and/or a hydrocarbon feed and have a particle size from 20 nm to 100 nm for the regular furnace or channel black or from 150 to 530 nm for the thermal black. The level of carbon black in the compounded elastomeric
10 material may range from 10 to 300 parts per 100 parts of elastomeric polymer (phr). 160 phr of carbon black is used in the example below.

Processing oil, preferably paraffinic, may be added to adjust both the viscosity of the elastomeric material compound for good processing and its hardness to within a range of 50 to 85 Shore A. The level of processing oil in the
15 compound elastomeric material may be in the range of from 0 to 200 parts per hundred of elastomeric polymer (phr). 57 to 65 phr of processing oil is used in the example below.

Mineral filler can be used. It is typically calcium carbonate, preferably used in quantities from 0 to 150 phr. Silica, aluminium silicate and magnesium
20 silicate are also used as fillers and other fillers are well known to the person skilled in the art. A silica-type filler is used in the example below at 15 phr.

Zinc oxide and stearic acid may added to activate any accelerators and attain a good cross-link density. Typical quantities are between 0 to 20 phr of zinc
oxide and 0 to 5 phr of stearic acid. In the example below, those materials are
25 used at 5 and 0.5 phr, respectively.

Polyethylene glycol may be used as a process aid and to activate the vulcanizing effect. Typical quantities are between 0 to 10 phr. The polyethylene glycols preferably have a molecular weight between 100 and 100000. 2 phr of polyethylene glycol having a molecular weight of 3350 MW is used in the
30 example below.

Vulcanizing agents may be used to cause a chemical reaction resulting in

cross-linking of the elastomer polymer chains. Typical are sulphur (0 to 10 phr), and sulfur donors such as thiuram disulfides (e.g tetramethylthiuramdisulfide) and thiomorpholines (e.g dithiodimorpholine) in the range of 0 to 10 phr. Accelerators are used to reduce the vulcanization time by increasing the speed of the cross-
5 linking reaction. They are typically thiazoles such as 2-mercaptobenzothiazole or mercaptobenzothiazol disulfide, guanidines such as diphenylguanidine, sulfenamides such as N-cyclohexylbenzothiazolsulfenamide, dithiocarbamates such as zincdimethyldithiocarbamate, zincdiethyldithiocarbamate, and zincdibutyldithiocarbamate, thioureas such as 1,3-diethylthiourea, thiophosphates
10 and others well known to the one skilled in the art of rubber compounding. All can be used in the range of 0 to 5 phr. Sulfur, sulphenamide, carbamate and thiazole are used in the example below.

Protective agents may be included in elastomeric material to improve its aging performance and resistance to heat, light and ozone. For example, Agerite
15 Resin D is polymerised 1,2-dihydro-2,2,4-trimethylquinoline from R.T Vanderbilt, and Winstay 100 is a phenylene diamine from R.T Vanderbilt. None are used in the example below.

Other additives, especially those typically used in the art or described in the literature, may be present in the elastomeric materials of either or both
20 members of the shaped structure of the invention, for example, processing aids, antioxidants, stabilizers, anticorrosion agents, UV absorbers, antistatics, slip agents, and pigments, dyes and other colorants. Polyethylene wax, petroleum resin (C5-C9) and moisture absorbant (calcium oxide) are used in the example below.

Where the material is to be cross-linked, cross-linking agents such as those
25 mentioned above appropriate to the material and the cross-linking method may be incorporated.

The term "elastomeric material" as used herein can refer to both an elastomeric polymer material, such as an EPDM or a TPE, or to a compounded material containing one or more additives depending on the context. The term
30 "EPDM material" refers to a compounded material comprising an EPDM. The term "TPE" refers both to the TPE as such, which is typically a dynamically

vulcanised EPDM finely dispersed in a thermoplastic continuous matrix such as polypropylene, and also to a compounded material comprising a TPE and one or more ingredients such as filler (e.g. clay, talc and calcium carbonate), oil, various plastic materials (e.g. polyethylene, polypropylene of different composition, MW or MW distribution and styrenic resins) that are used to modify and optimize the properties/processing of the TPE. The terms “parts per hundred rubber” (phr) and “parts per hundred elastomeric polymer” are equivalent as used herein.

The modifier may be used, for example, in a proportion of up to 50%, advantageously in a range of from 1% to 40%, more advantageously from 2% to 35%, and preferably from 5 to 20% by weight, based on the weight of the elastomeric material. The modifier may be used alone or in combination with one or more other plasticizers, especially a plasticizing polymer, for example a low molecular weight polyethylene or ethylene copolymer, e.g. an ethylene alpha-olefin copolymer or plasticizing resin. Unlike certain mineral oil plasticizers, the selected modifier typically does not migrate to the surface, or bleed out, in processing or use.

Non-polymeric plasticizers may, however, be present. For example, mineral oil as in the example below or the phthalate, adipate, and trimellitate esters of alkanols, especially alkanols of from four to twelve carbon atoms, commonly used to plasticize polymers may be used, provided that in the polymer concerned they do not bleed out.

In a preferred embodiment, the shaped structure is a weatherseal, for example, an automobile weatherseal. The weatherseal may comprise a first member of an EPDM material comprising a modifier and a second member of TPE material adhering to the first member. The weatherseal may comprise a third member of EPDM material and the second member may serve to join the first and third members together in a joint.

The process of the invention preferably involves molding in the shaping of the first member and/or in the applying of the second elastomeric material to the first member. Suitable molding techniques include transfer molding, injection molding and compression molding. The process of the invention may involve

lamination of the first and second elastomeric materials, for example, by co-extrusion.

The process of the second aspect of the invention may be a process of making a weatherseal. Advantageously, the first member is made by extruding the first elastomeric material and cutting the extruded material into the desired length. Advantageously, the first elastomeric material is an EPDM material which is cured during or shortly after the extrusion step and prior to the cutting step. Preferably, the second elastomeric material is a TPE material. Advantageously, the second elastomeric material is injection molded onto the first member.

The applications of the shaped structures of the invention include all those where the properties or characteristics of one member differ from those of another, either in manufacture or use. As examples there may be mentioned as applications electrical apparatus, e.g., wire and cable, building and construction seals, e.g., in windows, concrete slabs and pipes, toys, sporting equipment, medical devices, outdoor furniture and automotive components. As examples of the latter, there may be mentioned bumpers, grills, interior and exterior trims, dashboard and instrument panels, spoilers, door and hood components, hoses, mirror housings, and especially weatherseals, for example glass run channels, door seals, belt line seals, insulation seals, roof seals, trunk seals, and hood seals. Other seals in automotive applications include those used to insulate parts from air, water, dust, and vibration, and interiors from noise and vibration. Other automotive applications include hoses, pipes, tubes and windscreen wipers.

In a third aspect, the invention provides the use in a structure comprising a first member comprising a first elastomeric material and a second member comprising a second elastomeric material, different from the first, of a modifier as defined above in combination with the first elastomeric material to improve adhesion between the first and second members.

The following example is provided for the purpose of illustration only:

A comparative elastomeric material A and an elastomeric material B according to the invention were prepared having the compositions shown in Table 1.

	A	B
Vistalon 7500 (EPDM)	100	100
Spheron 5000 carbon black	160	160
Flexon 815 plasticizer	57	30
Spectrasyn 100 plasticizer		35
Sillitin Z mineral filler	15	15
PEG 3350	2	2
PE wax	7	7
Escorez 1102	10	
Zinc oxide	5	5
Stearic Acid	0.5	0.5
Calcium Oxide (Rhenogram Ca0-80)	7	7
Sulfur	1.5	1.5
CBS (N-cyclohexylbenzothiazol sulphenamide)	1.5	1.5
ZBEC (70%)	1.3	1.3
VulKalent E	0.5	0.5
MBTS (80%) (mercaptobenzothiazol disulphide)	1	1
Total, phr	369.3	367.3

Table 1: Composition of comparative elastomeric material A and example elastomeric material B

5

Vistalon 7500 is a bimodal EPDM polymer available from ExxonMobil Chemical.

Spectrasyn 100 is a polyalphaolefin having a kinematic viscosity at 100°C of 100.0 cSt available from ExxonMobil Chemical.

Sillitin Z is semi-reinforcing filler comprising a natural blend of quartz and kaolinite available from Hoffman Mineral of Germany.

Escorez 1102 is C5-C9 petroleum resin available from ExxonMobil Chemical, ZBEC is a zinc carbamate curative and VulKalent E is a curing
5 retarder, available from RheinChemie.

EPDM materials A and B were extruded in a flat strip of 3mm thickness from a screw extruder having a barrel temperature of 65-70°C and a die temperature of 90°C. The temperature of the EPDM material leaving the extruder was in the region of 105-110°C. The extruded strip was then conveyed through a
10 microwave oven and a hot air tunnel for vulcanization.

The cured EPDM strip was set in a mold and a commercially-available TPE-V, Santoprene 121-65 W233, which does not contain any PAO, was injection molded onto it so that it adhered onto the edge of the EPDM material strip to form a sheet having an EPDM material/TPE interface. A dumbbell-shaped specimen
15 was then cut from the sheet with the interface located at about the middle of the narrow portion of the dumbbell. The adhesion at the interface was tested by pulling the specimen in a tensometer until delamination occurred at the interface. The test was carried out at three temperatures.

Properties of Santoprene 121-65 W233 are given in Table 2.

Property	Referenced Test Method	Test Unit	Typical Value
Hardness		Shore A	
5s*	ASTM D 2240		65
15 s	ISO 868		69
Density	ISO 1183/ASTM D 792	g/cm ³	0.92
Tensile strength at break**	ISO 37/ASTM D 412	Mpa (psi)	5.2 (750)
Elongation at break**	ISO 37/ASTM D 412	%	525
Tensile stress at 100% elongation**	ISO 37/ASTM D 412	Mpa (psi)	2.0 (290)
Compression set, 22 hrs., 25% deflection	ISO 815, Type A/ASTM D 395, Method B, Type 1	%@23°C (73°F)	20
		%@70°C (158°F)	45

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080")

5 * Value is for injection molded plaque, side-gated 82.6 mm x 117.5 mm x 3.0 mm (3.250" x 4.625" x 0.120")

** Physical properties are measured across the flow direction – ISO type 1, ASTM die C

10 Table 2: Some properties of Santoprene 121-65 W233

The results of the adhesion test are given in Table 3.

Adhesion on Santoprene 121-65 W233		cpd A	cpd B
Room Temperature, TS std dev.	MPa	2.08 0.12	2.44 0.32
80°C, TS std dev.	MPa	0.98 0.10	0.90 0.03
-10°C, TS std dev.	MPa	3.97 0.05	4.47 0.35

5 Table 3: Adhesion results for specimens comprising EPDM material A or B
molded on Santoprene 121-65 W233 TPE

As can be seen from Table 3, EPDM material A,
comprising a polyolefin, shows improved adhesion onto a TPE at room
10 temperature and at -10°C, as compared to EPDM material B, comprising as
plasticizer only a conventional paraffinic oil. No effect was seen at 80°C.

CLAIMS

1. A structure comprising a first member of a first elastomeric material and a second member of a second elastomeric material, different from the first, adhering
5 to the first member, wherein at least the first member comprises a modifier which comprises carbon and hydrogen, and does not contain an appreciable extent of functional groups and has one or more of the following characteristics:
- a. a pour point (ASTM D97) of -10°C or less;
 - b. Viscosity Index (VI) as measured by ASTM D2270 of 120 or more;
 - 10 c. a flash point (ASTM D92) of 200°C or more;
 - d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.
2. A structure as claimed in claim 1, in which the second member also comprises a modifier.
- 15
3. A structure as claimed in claim 1 or claim 2, wherein the modifier has c. a flash point (ASTM D92) of 200°C or more, and one or more of:
- a. a pour point (ASTM D97) of -10°C or less;
 - b. Viscosity Index (VI) as measured by ASTM D2270 of 120 or more;
 - 20 d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.
4. A structure as claimed in any preceding claim, wherein the modifier has:
- b. Viscosity Index (VI) as measured by ASTM D2270 of 120 or more; and
 - d. a specific gravity (ASTM D4052, 15.6/15.6oC) of 0.88 or less.
- 25
5. A structure as claimed in any preceding claim, wherein the modifier comprises one or more of:
- v) a polyalphaolefin;
 - vi) a hydrocarbon fluid with a branched paraffin: normal paraffin ratio
30 ranging from 0.5:1 to 9:1;
 - vii) a Group III hydrocarbon basestock;

viii) a basestock derived from a Fischer-Tropsch hydrocarbon product.

6. A structure as claimed in claim 5 wherein the modifier comprises polyalphaolefin.

5

7. A structure as claimed in claim 6, in which the modifier comprises a polyalphaolefin which is an oligomer of an alphaolefin having from 5 to 14 carbon atoms.

10 8. A structure as claimed in any preceding claim in which the first elastomeric material is an EPDM material.

9. A structure as claimed in any preceding claim in which the second elastomeric material is a TPE.

15

10. A structure as claimed in any preceding claim in which the first member comprises up to 50% by weight polyalphaolefin.

11. A structure as claimed in claim 2 in which the second elastomeric material
20 comprises up to 50% by weight polyalphaolefin.

12. A structure according to any preceding claim which is a weatherseal.

13. A process of making a shaped elastomeric structure comprising the steps
25 of compounding and shaping a first elastomeric material and a modifier as defined in claim 1 to give a first member and then applying onto that first member a second elastomeric material to give a second member adhering to the first member.

30 14. A process as claimed in claim 13 in which the first member is made by extrusion and cutting the extruded material into the desired length.

15. A process as claimed in claim 13 or claim 14 in which the second elastomeric material is molded onto the first member.

- 5 16. The use, in a shaped structure comprising a first member comprising a first elastomeric material and a second member comprising a second elastomeric material, different from the first, of a modifier as defined in claim 1 in combination with the first elastomeric material to improve adhesion between the first and second members.

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 December 2006 (07.12.2006)

PCT

(10) International Publication Number
WO 2006/128646 A3

(51) International Patent Classification:

C08L 23/00 (2006.01) *B60J 10/00* (2006.01)
B32B 25/14 (2006.01) *C08L 23/16* (2006.01)
B32B 27/32 (2006.01)

(21) International Application Number:

PCT/EP2006/005064

(22) International Filing Date: 24 May 2006 (24.05.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

0511320.4 3 June 2005 (03.06.2005) GB

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS INC.** [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US).

(71) Applicant (for GB only): **EXXONMOBIL CHEMICAL LIMITED** [GB/GB]; P.O. Box 122, 4600 Parkway, Solent Business Park, Whiteley Fareham, Hampshire PO15 7AP (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **JOURDAIN, Eric** [FR/BE]; Avenue Simonne 22, B-1640 Rhode Saint Genese (BE).

(74) Agent: **VELDHUIZEN, A., D., W.**; ExxonMobil Chemical Europe Inc., P.O. Box 105, B-1830 Machelen (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:

18 January 2007

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/128646 A3

(54) Title: ELASTOMERIC STRUCTURES

(57) Abstract: The invention relates to elastomeric structures comprising first and second members, each of a different elastomeric material, in which the first member includes a modifier. The shaped structure may be, for example, an automotive weatherseal.

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08L23/00 B32B25/14 B32B27/32 B60J10/00 C08L23/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B32B B60J C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 02/051634 A (EXXONMOBIL CHEM PATENTS INC [US]; JOURDAIN ERIC [BE]; SCHAUDER JEAN [B]) 4 July 2002 (2002-07-04) page 5, line 23 - page 10, line 20; claims 1-22; examples 1,2	1-16
Y	US 2004/106723 A1 (YANG HENRY WU-HSIANG [US] ET AL) 3 June 2004 (2004-06-03) paragraphs [0050] - [0080], [0226]; claims 1-15	1-16
Y	US 4 537 825 A (YARDLEY JAMES F [GB]) 27 August 1985 (1985-08-27) column 2, lines 53-62; claims 1,2; examples 1-3	1-16
Y	US 2004/054040 A1 (LIN CHON YIE [US] ET AL) 18 March 2004 (2004-03-18) paragraphs [0042] - [0056]	1-16

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

29 November 2006

Date of mailing of the international search report

05/12/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Adams, Florian

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 02051634	A	04-07-2002	EP 1355785 A1	29-10-2003
			JP 2004524183 T	12-08-2004
			US 2004059061 A1	25-03-2004
<hr/>				
US 2004106723	A1	03-06-2004	US 2006189763 A1	24-08-2006
<hr/>				
US 4537825	A	27-08-1985	AU 2040683 A	03-05-1984
			EP 0116747 A1	29-08-1984
			IN 157880 A1	12-07-1986
			JP 59095137 A	01-06-1984
			NZ 205950 A	11-06-1986
			ZA 8307734 A	29-05-1985
			ZW 22383 A1	11-01-1984
<hr/>				
US 2004054040	A1	18-03-2004	AU 2003258173 A1	25-02-2004
			BR 0313549 A	21-06-2005
			JP 2006508236 T	09-03-2006
			WO 2004014998 A2	19-02-2004
			US 2006205863 A1	14-09-2006